

Sub  
C7  
cont

~~2. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the melt flow rate (MFR<sub>2</sub>) (230°C, 2.16 kg) of the polyolefin is greater than 1, and preferably from about 10-18g/10 min.~~

3. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the pressure pipe (20) is a pressure pipe, the pressure category of which is PN 16 or higher according to standard ISO 4065.

4. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the polyolefin is polypropylene, and wherein the long-fiber reinforcements are glass fibers.

5. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the length of the long-fiber reinforcements is at least 30 times the fiber diameter.

6. (Amended) A multi-layer pressure pipe (20) according to wherein the length of the long-fiber reinforcements in the pressure pipe is on the order of magnitude of from about 0.5-50 mm, preferably from about 1-20 mm, and most preferably from about 2-15 mm.

*Sub  
C7  
cond*

~~7. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the amount of long-fiber reinforcements ranges from about 5 to 95% by weight, and preferably from about 25 to 75% by weight.~~

*B1  
bullet*

8. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the pressure pipe (20) has a double-layer structure.

9. (Amended) A multi-layer pressure pipe (20) according to claim 1, wherein the pressure pipe (20) has a four-layer structure.

---

FOR FURTHER INFORMATION